





## QM-PPGWRP:

Everyday gloss high density microporous polypropylene

Producing long lasting banners with superior tear resistance, its microporous coating gives it the ability to reproduce true high quality photographic images with rich black inks.



## **Benefits:**

- Economical
- Wide Color Gamut
- Water Resistant
- Tear Resistant

## **Applications**

- POP Displays
- Indoor Banners
- Photo Displays
- Short Term Outdoor Signage



| TECHNICAL DATA:    |                            |                      |  |
|--------------------|----------------------------|----------------------|--|
| SURFACE FINISH:    | Gloss                      | OPACITY:             | 98                                     |
| BASE MATERIAL:     | Polypropylene              | DURABILITY:          | Indoor: Up to 1 year Outdoor: 6 months |
| BASE WEIGHT:       | 163 GSM +/- 10%            | ROLL LENGTH:         | 100 FT, 200 FT.                        |
| CALIPER:           | 8 MIL +/- 1                | ROLL WIDTHS:         | 24", 36", 42", 50", & 60"              |
| BRIGHTNESS:        | 89 (ISO Blue Whiteness)    | CORE:                | 3" with 2" adapter                     |
| WHITENESS:         | 90 (CIE Ganz)              | PRINT SIDE:          | Print Side Out                         |
| GLOSS MEASUREMENT: | 29 +/- 10% by angle of 60° | INK RECOMMENDATIONS: | AQUEOUS LILATEX UV UV                  |



This media is designed for digital printing applications using OEM printers with their accompanying OEM ink sets. Although designed for all printers using the aforementioned OEM matching ink sets; actual results may vary depending on printer model, age, print design, environmental conditions, and other factors. Exposure of a print to atmospheric pollutants, or to temperature, humidity, and / or lighting extremes can result in fading, color shifting, or other visual changes. The ideal conditions for printing and storage are a temperature of 70°F ±5°F and relative humidity of 50% RH ±3% RH. Our wide format media is guaranteed against manufacturing flaws and defects and is designed to resist printer jams when used properly. Storage: Up to one year if stored in proper conditions (cool, dry place 50-80°)

