



**QM-SATCAN:**

Professional satin solvent coated polyester/cotton canvas

This polyester/cotton canvas provides a consistent satin printing surface that allows for an extremely wide color gamut, rich black densities, and great tonal range. It has a consistent 2 over 1 Oxford weave giving it the traditional artist's texture look and feel. With this finish, printmakers can reproduce anything from portraits to landscapes. OBA-Free and acid neutral, making it a go-to product for any EcoSolvent, latex or uv printer requiring a durable, archival grade canvas.



**Benefits:**

- 35% Cotton/65% Polyester
- Anti-Sag Weave
- True Archival
- OBA Free Coating
- Neutral Satin Coating

**Applications:**

- Museum And Gallery Prints
- Home Décor Printing
- Photo Reproduction
- Gallery Stretched Giclee's
- Framed Art



TECHNICAL DATA:			
SURFACE FINISH:	Satin	OPACITY:	97
BASE MATERIAL:	35% Cotton/65% Polyester	GLOSS MEASUREMENT:	6 +/- 10% by angle of 60°
FABRIC WEAVE:	Oxford 2 over 1	DURABILITY:	Indoor: Up to 1 year Outdoor: 6 months
BASE WEIGHT:	380 GSM +/- 10%	ROLL LENGTH:	65 FT.
CALIPER:	20 Mil +/- 2	ROLL WIDTHS:	54"
BRIGHTNESS:	91 (ISO Blue Whiteness)	CORE:	3"
WHITENESS:	120 (CIE Ganz)	INK RECOMMENDATIONS:	ES ECO-SOLVENT L LATEX UV UV



This media is designed for digital printing applications using OEM printers with their accompanying OEM ink sets. Although designed for all printers using the aforementioned OEM matching ink sets; actual results may vary depending on printer model, age, print design, environmental conditions, and other factors. Exposure of a print to atmospheric pollutants, or to temperature, humidity, and / or lighting extremes can result in fading, color shifting, or other visual changes. The ideal conditions for printing and storage are a temperature of 70°F ±5°F and relative humidity of 50% RH ±3% RH. Our wide format media is guaranteed against manufacturing flaws and defects and is designed to resist printer jams when used properly. Storage: Up to one year if stored in proper conditions (cool, dry place 50-80°)

